

Our Ref: SW/LS/JM

15 October 2019

**Report 351394**


**Page 1 of 3**

Ambassador Textiles Ltd.  
Unit A Vulcan Point  
Vulcan Street  
Oldham  
OL1 4DR

Contact: Diane O'Connell

DATE RECEIVED : 30 SEP 2019  
QUALITY/REFERENCE : MARBLE VELOUR  
REPUTED FIBRE CONTENT : 100% POLYESTER  
FABRIC DESCRIPTION : WOVEN  
COLOUR/DESIGN : RUBY

PERFORMANCE STANDARD : BS2543:2004 & BSEN 14465:2003 + A1:2006



**REPORT SUMMARY**

Tests	Method	Pass	Fail	Requirement
Abrasion of upholstery	Abrasion Resistance BS EN ISO 12947-2: 1998 / BS EN 14465: 2003 Annex A	Pass		Level A Suitable for any end use.



**S. WISEMAN**  
**LABORATORY DIRECTOR**



**L. SHERIDAN**  
**LABORATORY MANAGER**



118 Lupton Avenue Leeds LS9 6ED  
Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 Email: [info@hstts.co.uk](mailto:info@hstts.co.uk)  
Registered No. 2899980 VAT No. 613 4310 86

15 October 2019

**Report 351394**

**Page 2 of 3**

*This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.*



118 Lupton Avenue Leeds LS9 6ED  
Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: [info@hstts.co.uk](mailto:info@hstts.co.uk)  
Registered No. 2899980 VAT No. 613 4310 86

15 October 2019

**Report 351394**

**Page 3 of 3**

**PHYSICAL**

**Abrasion Resistance BS EN ISO 12947-2: 1998 / BS EN 14465: 2003 Annex A**  
12 kPa load.

Requirement:

Level A Suitable for any  
end use.

Number of rubs to breakdown:
Head 1 45,000
Head 2 45,000
Head 3 45,000
Head 4 45,000

