

Our Ref: SW/JM

12 March 2020

Report 360528

Page 1 of 3

Ambassador Textiles Ltd.
Unit A Vulcan Point
Vulcan Street
Oldham
OL1 4DR

Contact: Diane O'Connell

DATE RECEIVED	: 6 MAR 2020
FABRIC SUPPLIER	: AMBASSADOR TEXTILES
QUALITY/REFERENCE	: SYDNEY
REPUTED FIBRE CONTENT	: 100% POLYESTER
FABRIC DESCRIPTION	: WOVEN
COLOUR/DESIGN	: AMBSYDNEY 05 (BEIGE)
STYLE NUMBER	: XDR2011
END USE	: FURNISHINGS
ORDER NUMBER	: DIANE/SYDNEY
PERFORMANCE STANDARD	: BS2543 & BS EN 14465:2003 + A12006



REPORT SUMMARY

Tests	Method	Pass	Fail	Requirement
Colour fastness to washing	BS EN ISO 105-C06: 2010	Pass		Level A suitable for Any End Use
Abrasion of upholstery	Abrasion Resistance BS EN ISO 12947-2: 1998 / BS EN 14465: 2003 Annex A	Pass		Level A suitable for Any End Use



118 Lupton Avenue Leeds LS9 6ED
Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: info@hstts.co.uk
Registered No. 2899980 VAT No. 613 4310 86

12 March 2020

Report 360528

Page 2 of 3



S. WISEMAN
LABORATORY DIRECTOR

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.



118 Lupton Avenue Leeds LS9 6ED
Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: info@hstts.co.uk
Registered No. 2899980 VAT No. 613 4310 86

12 March 2020

Report 360528

Page 3 of 3

COLOUR FASTNESS TO:

BS EN ISO 105-C06: 2010 A2S 40°C Washing

	S/C	Ate.	Cot.	Nyl.	Pol.	Acr.	Wool
	4-5	4-5	4-5	4-5	4-5	4-5	4-5

Requirement:
Level A suitable for Any
End Use

PHYSICAL

Abrasion Resistance BS EN ISO 12947-2: 1998 / BS EN 14465: 2003 Annex A ~
12 kPa load.

Number of rubs to breakdown:
Head 1 45,000
Head 2 45,000
Head 3 45,000
Head 4 45,000
Shade change after 3,000 rubs: 4-5

Requirement:
Level A suitable for Any
End Use

Tests indicated § are within the bounds of the flexible scope of accreditation operated by the laboratory.

