

Our Ref: SW/BR

12 August 2020

Report 364712

Page 1 of 3

Ambassador Textiles Ltd.
Unit A Vulcan Point
Vulcan Street
Oldham
OL1 4DR

Contact: Diane O'Connell

| | |
|-----------------------|---|
| DATE RECEIVED | : 11 AUG 2020 |
| FABRIC SUPPLIER | : AMBASSADOR TEXTILES |
| QUALITY/REFERENCE | : 225 FAUX SUEDE |
| REPUTED FIBRE CONTENT | : 100% POLYESTER |
| FABRIC DESCRIPTION | : WOVEN |
| COLOUR/DESIGN | : STONE |
| END USE | : FURNISHINGS |
| ORDER NUMBER | : DIANE/DAR02 |
| PERFORMANCE STANDARD | : BS 2543:2004 & BS EN 14465:2003 + A1:2006 |



REPORT SUMMARY

| Tests | Method | Pass | Fail | Requirement |
|----------------------------|-------------------------|------|------|----------------------------------|
| Colour fastness to washing | BS EN ISO 105-C06: 2010 | Pass | | Level A suitable for Any End Use |
| Colour fastness to rubbing | BS EN ISO 105-X12:2016 | Pass | | Level A suitable for Any End Use |
| Colour fastness to rubbing | BS EN ISO 105-X12:2016 | Pass | | Level A suitable for Any End Use |



118 Lupton Avenue Leeds LS9 6ED
Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: info@hstts.co.uk
Registered No. 2899980 VAT No. 613 4310 86

12 August 2020

Report 364712

Page 2 of 3



S. WISEMAN
LABORATORY DIRECTOR

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.



118 Lupton Avenue Leeds LS9 6ED
Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: info@hstts.co.uk
Registered No. 2899980 VAT No. 613 4310 86

12 August 2020

Report 364712

Page 3 of 3

COLOUR FASTNESS TO:

BS EN ISO 105-C06: 2010 A2S 40°C Washing

| | S/C | Ate. | Cot. | Nyl. | Pol. | Acr. | Wool |
|--|-----|------|------|------|------|------|------|
| | 4-5 | 4-5 | 4-5 | 4-5 | 4-5 | 4-5 | 4-5 |

Requirement:
Level A suitable for Any
End Use

BS EN ISO 105-X12:2016 Dry Rubbing

| Colour | Test | Staining |
|--------|-------------------|----------|
| | Dry, Face, Length | 4-5 |
| | Dry, Face, Width | 4-5 |

Requirement:
Level A suitable for Any
End Use

BS EN ISO 105-X12:2016 Wet Rubbing

| Colour | Test | Staining |
|--------|-------------------|----------|
| | Wet, Face, Length | 4-5 |
| | Wet, Face, Width | 4-5 |

Requirement:
Level A suitable for Any
End Use

