

Our Ref: SW/RM

24 February 2020

Report 359057

Page 1 of 3

Ambassador Textiles Ltd. Unit A Vulcan Point Vulcan Street Oldham OL1 4DR

Contact: Diane O'Connell

DATE RECEIVED QUALITY/REFERENCE REPUTED FIBRE CONTENT

COLOUR/DESIGN

END USE

ORDER NUMBER

: 11 FEB 2020

: AVALON

: 100% POLYESTER

: GREY

: UPHOLSTERY

: 5551

PERFORMANCE STANDARD

: BS2543:2004 & BSEN 14465:2003 + A1:2006



REPORT SUMMARY

Tests	Method	Pass	Fail	Requirement
Abrasion of upholstery	Abrasion Resistance BS EN	Pass		Level A suitable for Any End
	ISO 12947-2: 1998 / BS EN			Use
	14465: 2003 Annex A			

S. WISEMAN LABORATORY DIRECTOR



118 Lupton Avenue Leeds LS9 6ED
Tel:0044 (0) 113 248 8830 Fax:0044 (0) 113 248 0239 EMail: info@hstts.co.uk
Registered No. 2899980 VAT No. 613 4310 86



24 February 2020

<u>Page 2 of 3</u>

This report may not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method, preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.





24 February 2020

Report 359057

Page 3 of 3

PHYSICAL

Abrasion Resistance BS EN ISO 12947-2: 1998 / BS EN 14465: 2003 Annex A

Number of rubs to break	down:
Head 1 50,000	
Head 2 50,000	
Head 3 50,000	
Head 4 50,000	
Shade change after 3,00	0 rubs: 4-5

Requirement:

Level A suitable for Any End Use



